



MAXIDURA - CI - 113

EXTREMELY CRACK RESISTANT NICKEL ALLOY ELECTRODE FOR WELDING CAST IRON..

ALLOY BASIS

Fe, Ni,

PROPERTIES

Electrode with excellent welding characteristics. The deposit is machinable and crack proof. Good bonding on difficult to weld cast iron. Ideal for CI to MS welding and CI to CI Welding

TECHNICAL DATA

HARDNESS	150-190
UTS of Joint	35-45Kgf/mm ²

TYPICAL APPLICATIONS

Hot and Cold welding of cast iron parts of gray cast iron, nodular graphite iron, malleable iron subject to heavy wear. Joining of cast material with steel. The electrode is most suitable for the surface of above material. Casting, Machinery parts, bearing blocks, frames, foundry casting etc.

WELDING CURRENT

CURRENT	AC/DC(+)	
Size (mm)/Length	3.15x350	4.0x350
Current(amps)	90-120	120-160

SHRI BALAJI ALLOYS CORPORATION INDIA

HEADOFFICE:-HD68A, NEAR ADARSH CHOWK, KABIR NAGAR, RAIPUR (CHHATISGARH), 492001.

PHONE/FAX:-07714905001

OUR-BRANCES:-INDORE&HYDERABAD.

